

# **Product Data Sheet**

# **Red Oxide Primer - 2651**

# **Product Description**

This product is a moderately fast drying shop primer.

# Where to Use

Surfaces that need quick drying and quick recoating with a rust inhibitive iron oxide. It has moderate weatherability but should be topcoated for best results

#### **Product Characteristics**

Color Red

Gloss Low Sheen

Architectural and Industrial

Not Intended For Residential Use, Shop Use Only Maintenance Category

Temperature To Touch To Recoat **Drying Time** 75°F / 55% R.H. 1 Hour 8 Hours

(Cooler temperatures and higher humidity will lengthen drying time)

#### Preparation & Priming

Surface Preparation For maximum performance, the recommended substrate should be blasted in accordance with SSPC-SP7. If

> blast cleaning is not feasible, the substrate should be degreased in accordance with SSPC-SP1. All burrs should be removed and sharp edges or rough weld seams should be ground down. Full use should then be made of mechanical power tools, in conjunction with wire brushing and chipping to remove all loose rust and

mill scale to a standard of cleanliness conforming to SP-2 or SP-3.

Finish Coats Typical topcoats include industrial enamels such as Anchor #0900 series and #0500 series. Consult your

Anchor representative for specific job recommendations.

### Mixing & Application

Stir thoroughly, making sure no pigment remains on the bottom of the can. Mixing

Use Anchor #J1131 for spray applications or #J1112 for brush and roller usage; only thin if permitted by **Thinning** 

federal, state and local regulations

Minimum 40°F, Maximum 110°F - The surface should be dry and the relative humidity should be no greater Surface Temperature

than 85%.

**Brush** 

1.6-2.0 mils dry minimum Recommended Thickness

742 ft2/gal at 1 mil dry, assuming no application losses. Coverage will vary depending on the color, **Theoretical Coverage** 

application technique, porosity and design of the substrate.

Ft2/gal Wet Mils Dry Mils Coverage Rates per Coat

412 Suggested 18 39 1.6 3.5 464 **Minimum Maximum** 2.0 4.3 371

1200-2200 psi Application Equipment Airless Spray Pressure

> 0.011"-0.015" Air Pressure 60-80 psi

Conventional Spray Fluid Pressure 10-20 psi

Use a high quality natural china bristle brush.

Roller Use a 1/4" Synthetic nap roller cover.

**Application Considerations** The recommended method of application is by airless spray. However, brush, roller, or conventional spray may

also be used. To avoid dusting, apply in wet coats. On a derusted surface the application of a dry film

thickness of at least 2 mils is recommended. With any oxidative coating, faster dry time may be obtained with

increased air movement and/or higher substrate or material temperature.

#### **Technical Information**

Solids by Volume 46.24%

Actual VOC 3.44 lb/gal (412 g/l)

<u>Density</u> 11.62 lb/gal (1392 g/l)

Packaging 55 Gallon drums, 5 Gallon pails and 1 Gallon cans

Physical Properties Alkalis: Poor Acids: Good Water: Very Good

#### Clean-up & Storage

Cleanup Use Anchor #J1131 synthetic thinner

Storage Temperature Minimum 20°F Maximum 110°F

<u>Shelf Life</u> Under Normal Conditions (Unopened) – Two Years

# Safety & Important Information

DANGER! EXTREMELY FLAMMABLE LIQUID AND VAPOR. CONTAINS: MINERAL SPIRITS AND PETROLEUM DISTILLATES. Vapor harmful. May affect the brain or nervous system causing dizziness, headache or nausea. Causes nose, eye, skin and throat irritation. NOTICE: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.

Vapors may ignite explosively. Keep away from heat, sparks and flame. Vapors may cause flash fire. Close container after each use. Do not smoke. Extinguish all flames and pilot lights, and turn off stoves, heaters, electric motors and other sources or ignition during use and until all vapors are gone. Prevent build-up of vapors by opening all windows and doors to achieve cross-ventilation. **Use only with adequate ventilation.** Do not breathe vapors or spray mist. Ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes, skin and clothing. Wash thoroughly after handling. **KEEP OUT OF REACH OF CHILDREN.** 

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. WARNING! Sanding or scraping pressure treated lumber may be hazardous; wear appropriate protection.

Version: 6/2017

LIMITED WARRANTY: The technical data on this label or on other data is true and accurate to the best of our knowledge. We guarantee our products to conform to ANCHOR PAINT MFG. CO. quality control standards. Due to misuse in handling, storage, application and workmanship or variables such as weather or surface integrity that are beyond our control, Anchor Paint does not authorize any representative to make any warranty or merchantability of fitness of this product. Any liability whatsoever of Anchor Paint Mfg. Co. to the buyer or user of this product is limited to the purchaser's cost of the product itself.